



~~Method for the Operation of a Sliding Closure as well as a~~, and the Sliding Closure

BACKGROUND OF THE INVENTION

The invention concerns a method for ~~the operation of a sliding closure for~~ metallurgic vessels, ~~whereby~~ wherein the said sliding closure incorporates at least opposingly tensionable fireproof closure plates which are each, slideably opposingly, positioned along glide surfaces within a housing part, and ~~whereby~~ wherein spring elements ~~are~~ are envisaged for the tensioning of the closure plates in at least one of the housing parts, and ~~whereby~~ wherein one closure plate with its housing part can be pushed moved into a closed, ~~i.e. or~~ open position by a drive member.

Sliding closures are ~~utilised~~ utilized especially for ~~the~~ pans or distribution containers of extrusion ~~moulding~~ molding plants for a controlled pouring of ~~the~~ steel smelt. The ~~f~~Fireproof closure plates and fireproof sleeves ~~utilised~~ utilized for these sliding closures, through which ~~the~~ liquid steel smelt flows, as well as ~~the~~ a mechanism supporting the same are subjected to relatively strong wear. The plates and sleeves must therefore be replaced frequently.

In order to achieve a high efficiency these fireproof parts are left within the sliding closure and used as long as possible. It has been demonstrated by operating personnel how ~~the~~ emptying of pans can sometimes be achieved with ~~the~~ aid of closure plates and sleeves with visual control and experience. In reality, however, it has been proven that breakouts occur due to incorrect estimates or insufficient control possibilities, where ~~the~~ steel smelt flows in an uncontrolled manner through the sliding closure and damages or even destroys the same. This applies also to incorrect assemblies of the sliding closure

where, for example, insufficient mortar has been installed between the fireproof parts.

BRIEF SUMMARY OF THE INVENTION

Based on the aforementioned it is ~~the~~ a purpose of this invention to provide a method for ~~the~~ operation of a sliding closure of the above mentioned type with which operational safety can be increased and possible imminent operational faults such as breakouts can be ~~recognised~~ recognized early.

This task is solved in accordance with the invention by ~~the~~ an ~~off-offline~~ and/or online diagnosis of ~~the~~ an operating condition, especially within ~~the~~ an area of the closure plates, with which one or more ~~dimensions relating to~~ of size, temperature, pressure and/or force ~~of associated with~~ the ~~a~~ sliding closure ~~are~~ is measured, and this measured value is evaluated either directly or together with additional relevant process parameters in order to be able to judge the operating condition, and therefore, also a possible continued use of the sliding closure.

~~The~~ A method of this invention enables ~~the~~ detection and prevention of operational faults and especially breakouts, during which ~~the entire~~ sliding closure mechanics in their entirety and possibly also parts of ~~the~~ an extrusion ~~moulding~~ molding plant are often destroyed, as ~~far~~ much as possible. Incorrect assemblies of the sliding closure especially can be detected and breakouts prevented in this way.

With a preferred embodiment, ~~the~~ a distance of ~~each of the~~ housing parts, receiving the closure plates, from one another in a ~~diagonal~~ transverse direction in relation to ~~the~~ plate glide surfaces is used as a ~~dimension~~ measured value, recorded, and transmitted to an evaluating ~~means~~ device, whereby ~~wherein said the~~ distance is preferably

measured in several places. ~~The~~ This measuring of the distance of these two housing parts from one another especially enables ~~the diagnosing of the a~~ position of ~~the a~~ closure plate with regard to changes in a ~~diagonal-transverse~~ direction relative to the glide surfaces, and therefore, ~~the~~ detection of sheets that may form between the plates.

~~The A~~ pressure of the drive member as well as ~~the a~~ stroke position of the slideable closure plate are preferably used as ~~the dimension~~ parameters that ~~is~~ are to be measured, i.e. recorded and evaluated, whereby ~~the frictional~~ relationships, and therefore ~~the a~~ condition of the closure plates especially, can be deduced from their contacting glide surfaces.

BRIEF DESCRIPTION OF THE DRAWINGS

Embodiments of the invention as well as further advantages of the same will now be described in more detail with reference to the drawings, ~~whereby~~ wherein:

Fig. 1 shows a schematic illustration of a sliding closure as well as an evaluating ~~means device~~ working according to ~~the a~~ method of this invention, and

Fig. 2 shows a cross-sectional view of a sliding closure with a measuring unit.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Fig. 1 shows a schematic illustration of a sliding closure 10 affixed to a metallurgical vessel 15 illustrated only in part, whereby the same consists, for example, of a pan of an extrusion ~~moulding~~ molding plant containing steel smelt. As part of the vessel 15 a steel jacket 11, a fireproof cladding 12, a perforated stone 14, as well as a fireproof sleeve 13 with an outlet 16 are shown.

The sliding closure 10 incorporates an upper housing part 17 into which a fireproof closure plate 21 is affixed. Within a further housing part 19 ~~the~~ a slideable closure ~~part~~ plate 22 is held, whereby the housing part 19 is held within a housing frame 18 and can be moved by a drive member 25 into an open position – as illustrated – or into a closed position. This drive member 25 takes the form of a hydraulic piston/cylinder unit and is therefore activated via pipes 26, 27 by a hydraulic aggregate 29. In addition the closure plates 21, 22 are pressed against one another by spring elements 23, so that an adequate seal is created between the ~~same~~ closure parts.

According to the invention, ~~the~~ a method for ~~the~~ operation of the sliding closure 10 incorporates an ~~off~~ offline and/or online diagnosis of ~~the~~ an operating condition, especially within ~~the~~ an area of the closure plates 21, 22, during which several ~~dimensions-values~~ with regard to size, temperature, pressure and/or force of the sliding closure 10 are measured and evaluated, either directly or together with additional relevant process parameters, in order to be able to judge the operating condition and therefore also a possible continued use of the sliding closure 10.

During ~~the~~ evaluation all ~~dimensions-values~~ measured as actual values are compared with a target value or a target value range, and a display or ~~such~~ the like for the checking or ~~the~~ emergency closure of the sliding closure is activated if deviations outside of ~~the~~ a tolerance limit are found to exist.

Within the context of the invention, ~~the~~ pressure of the drive member as well as ~~the~~ a stroke position of the slideable closure plate ~~is~~ are recorded and evaluated as one of the ~~dimensions-parameters~~ to be measured, whereby especially ~~the~~ frictional relationships, and therefore ~~the~~ a condition of the closure plates, can be judged in this way with ~~the~~ aid

of their contacting glide surfaces. For this purpose the supply lines 26, 27 of the cylinder are equipped with pressure sensors 28 which measure ~~the~~ actual pressure and supply corresponding signal values via electric cables 28' to an evaluating ~~means~~ device 20.

During ~~the~~ measuring of the pressure of the drive member conclusions regarding ~~the~~ frictional relationships of the plates 21, 22, depending upon ~~the~~ a stroke position of ~~the~~ sliding plate 22 in relation to ~~the~~ floor plate 21, and also regarding the application pressures of the spring elements 23, can be reached. If a deviation from ~~the~~ a relevant target value is detected ~~the~~ a pouring process can either be discontinued, or the sliding closure plate can be subjected to a suitable inspection following ~~the~~ conclusion of the pouring process, and a necessary replacement of the closure plates, or other defective parts, ~~carried out~~ is performed depending on ~~the~~ extent of ~~the~~ deviation. As soon as the measured values return to within ~~the~~ a tolerance value range following ~~the~~ inspection, the sliding closure can be used again.

Further ~~dimensions~~ measured values consist of ~~the~~ a temperature measured near the closure plates 21, 22. For this purpose the housing parts 17, 19 are equipped with measuring sensors 31, 32 at various points, whereby ~~the same~~ these sensors measure ~~the~~ actual temperatures and transmit the same via relevant electric cables 33, 34 to the evaluating ~~means~~ device 20. These temperature measurements enable ~~the~~ detection of possible leaks where liquid steel could exit between a plate and sleeve, or between the plates, as early as possible in order to avoid breakouts. As soon as at least one of these temperatures deviates from a predetermined value the closure can either be closed immediately or a message can be sent to request an inspection depending on ~~the~~ an extent of ~~the~~ this deviation.

Effectively, the evaluating ~~means-device~~ 20 incorporates a computer with a monitor 61 and a keyboard 62 for the programming and the menu-driven administration of the method. In addition, an emergency light 63 and an alarm 64 are envisaged, with which possible operational faults of the sliding closure can be audibly, i.e. visually notified. The evaluating ~~means-device~~ 20 could of course also be connected to an external computer, i.e. a central computer, located for example at a control ~~center~~ center.

In addition, the ~~an~~ application pressure of the spring elements 23 that tension the closure plates 21, 22 can be measured in order to determine whether one or more of the spring elements 23 are no longer functional. Such a measurement can be carried ~~outperformed~~ with the aid of an expansion measurement strip or a piezo element or ~~such~~ like.

These pressure measurements as well as the ~~temperature~~ measurements can be carried ~~outperformed~~ online, i.e. during the ~~a~~ pouring process, and/or offline, i.e. after the ~~a~~ pouring process, when the sliding closure has been positioned at an assembly location together with the pan.

The ~~A~~ target value or the ~~a~~ target value range of the ~~dimensions-parameters~~ that are to be measured can be adjusted with the aid of the additional process parameters ~~can be adjusted~~ during the use of the sliding closure. In this way it is, for example, possible that the wear of the glide surfaces, i.e. the flow passages, of the closure plates will have an effect on the temperatures detected by the measuring sensors 31, 32. In the same way it is possible that a temperature increase occurs during the use of the closure plates without any kind of defect being present. These changes are defined as the ~~kinds~~ of process parameters which are borne in mind during the evaluation of the measured

dimensionsvalues.

A further characteristic of the method of this invention envisages that a protocolling and a storing of ~~the measured~~ dimensions-values of the sliding closure will supply information regarding the pan and ~~the smelt~~ to be poured with regard to temperature, treatment, pouring time ~~ete~~and the like. These stored dimensions-values also serve as process parameters to be considered during ~~the evaluation~~, with which ~~the target~~ values are adjusted and a filtering process as part of ~~the comparison~~ of measured dimensions is ~~carried out~~performed with the target values in order to exclude false alarms as far much as possible.

Fig. 2 shows a sliding closure 40 which is described in detail in document WO-A-00/6325, of which only ~~the details~~ relevant to this invention are mentioned below. An upper housing part 47 affixed to a vessel 35 is envisaged here together with a closure plate 41 that can be affixed within the same, as well as a lower housing part 49, in which a fireproof closure plate 42 is held, which is moveably arranged vertically in relation to ~~the drawing~~ a plane of Fig. 2. Roller guides 44 are located on the upper housing part 47, through which the housing part 49 is guided within the same in a moveable way. The ~~s~~Spring elements effect ~~the movement of the lower~~ closure plate 42 towards ~~the upper~~ closure plate 41, ~~42~~ via these roller guides 44.

Within ~~the context~~ of the invention the housing parts 47, 49 are preferably equipped with two measuring sensors 50 on both sides, each arranged at a distance from the other, with which ~~the a~~ distance 53 of the two housing parts from one another in a ~~diagonal~~ transverse direction with relation to ~~the plate glide surfaces 41', 42'~~ is recorded and transmitted to ~~the evaluating means~~ device 20 via a relevant cable 51. These

measuring sensors 50 affixed to the upper housing part 47 each measure a distance 53 to a measuring element 52 affixed to the lower housing 49.

These measuring sensors 50 and measuring elements 52 are preferably encapsulated in a way not described in detail here, so that the same are protected against damage. ~~They~~ These sensors and elements can also be integrated directly into the housing parts 47, 49. In principle, a single measuring sensor 50 would also suffice.

With ~~the~~ measuring of these distances 53, i.e. ~~the~~ linear changes of the two housing parts 47, 49 in relation to one another, it is possible especially to diagnose ~~the~~ a position of the closure plates 41, 42 with regard to ~~diagonal~~ transverse changes in relation to the glide surfaces 41', 42'. If, for example, steel smelt enters between the plates a thin sheet can form there which can press the plates apart and therefore create a risk of an uncontrolled outpouring of steel smelt across the glide surfaces between these plates.

The invention has been described sufficiently with reference to the above embodiments. However, various other embodiments are possible.

In principle, the sliding closure could be evaluated with ~~the~~ aid of only one of the ~~dimensions~~ parameters described above, i.e. size, temperature, pressure and/or force, preferably in a programme-controlled ~~way~~ manner.